



Test Report

Determination of Attenuation Properties of Materials using Diagnostic X-Radiation

This test report may only be published in full, unless permission for the publication of an approved extract has been obtained in writing from NPL Management Ltd. It does not of itself impute to the subject of test any attributes beyond those shown by the data contained herein.

FOR:

Kemmetech Ltd
Unit 4, Arnold Business Park
Branbridges Road
East Peckham
Tonbridge
TN12 5LG
United Kingdom

DESCRIPTION:

Determination of Attenuation properties of Bi-Layer Lead Free Vinyl Material according to BS EN 61331-1:2014 using the modified Broad Beam Geometry (Eder and Schlattl, 2018¹)

DATE OF MEASUREMENTS: 19 September 2018

Reference: 2018110282_2

Date of Issue: 16 November 2018

Checked by: 

Signed: 

Name: G A Bass

Page 1 of 4

(Authorised signatory)

on behalf of NPLML

NATIONAL PHYSICAL LABORATORY

Continuation Sheet

CONDITIONS:

Distance from x-ray tube to target sample: 1.5m
Ionisation chamber used: PTW TW34069-2.5 s/n 000231

All equipment associated with the measurements performed in this report has direct traceability to UK national standards or UKAS accredited calibration facilities.

Table I
61331-1:2014 X-ray beam qualities

<u>X-ray Tube Voltage</u> kV	<u>Added filtration</u> mmAl*
60	2.5
70	2.5
90	2.5
110	2.5

*The inherent filtration of the x-ray tube was determined to be 0.3mmAl equivalent (according to ISO 4037-1:1996), giving a total filtration of 2.8mmAl

Reference: 2018110282_2

Checked by: 

Page 2 of 4

NATIONAL PHYSICAL LABORATORY

Continuation Sheet

RESULTS:

Table II

Bi-Layer Lead Free Vinyl, sample #62, 0.25mm nominal Lead equivalent
Measured Area density: 2.80 kg/m²

<u>kV</u>	<u>E_{mBBG}</u>	<u>δ_{mBBG}</u>	<u>PASS/FAIL†</u>
60	42.54	0.2408	PASS
70	23.10	0.2465	PASS
90	11.03	0.2534	PASS
110	7.041	0.2406	PASS

Table III

Bi-Layer Lead Free Vinyl, sample #63, 0.35mm nominal Lead equivalent
Measured Area density: 3.90 kg/m²

<u>kV</u>	<u>E_{mBBG}</u>	<u>δ_{mBBG}</u>	<u>PASS/FAIL†</u>
60	116.95	0.3392	PASS
70	50.96	0.3495	PASS
90	18.30	0.3510	PASS
110	11.05	0.3340	PASS

Table IV

Bi-Layer Lead Free Vinyl, sample #64, 0.5mm nominal Lead equivalent
Measured Area density: 5.68 kg/m²

<u>kV</u>	<u>E_{mBBG}</u>	<u>δ_{mBBG}</u>	<u>PASS/FAIL†</u>
60	513.67	0.5037	PASS
70	135.91	0.4970	PASS
90	35.68	0.5026	PASS
110	19.24	0.4659	PASS

†Determination of the lead equivalent class for a specified range of radiation qualities according to IEC 61331-1 clause 5.5.

Clause 5.5.3 of IEC 61331-1:2014 states that a relative standard uncertainty of 7% be taken into account in the decision of conformity in assigning the class of the Lead equivalent thickness to the material under test. If t_{pb} is the standard Lead equivalent thickness class (0.25mm, 0.35mm, 0.5mm or 1mm) and δ_{mBBG} is the Lead equivalence of the material under test, the condition can be written as:

$$\delta_{mBBG} \geq 0.93t_{pb}$$

Reference: 2018110282_2

Page 3 of 4

Checked by: 

NATIONAL PHYSICAL LABORATORY

Continuation Sheet

F_{mBBG} is the attenuation ratio in the modified Broad Beam geometry, given by:

$$F_{mBBG} = \frac{\dot{K}_0 - \dot{K}_B}{\dot{K}_1 - \dot{K}_B}$$

where \dot{K}_0 = Air Kerma Rate without the test object in the beam

\dot{K}_1 = Air Kerma Rate with the test object in the beam

\dot{K}_B = Background Air Kerma Rate with the test object replaced by a sheet of material with an attenuation ratio greater than 10^5 .

The Lead equivalent value δ_{mBBG} in mm using the Modified Broad Beam Geometry is obtained from fits to the attenuation curves F_{mBBG} of Lead foils of known thicknesses and of at least 99.995% purity.

UNCERTAINTIES

The uncertainty in the Lead equivalence value δ_{mBBG} is $\pm 5\%$. The reported expanded uncertainty is based on a standard uncertainty multiplied by a coverage factor $k = 2$, providing a level of confidence of approximately 95%.

REFERENCES

1. IEC 61331-1: A new setup for testing lead free X-ray protective clothing, Heinrich Eder and Helmut Schlattl, *Physica Medica* 45 (2018) 6–11

Reference: 2018110282_2

Checked by:



Page 4 of 4